

SNO	PARAMETER	SPECIFICATION
1	Appearance	Thixotropic pale yellow to yellow hazy liquid Free from agglomerates
2	Viscosity @ 25°C	9000 _± 2700cps
3	Acid Value (mgKOH/Gm)	25 _± 4
4	Gel Time @ 25°C Resin – 100 Gm; Cobalt Accelerator – 1.5 ml&MEKP Catalyst – 1.5 ml	18 _± 8
5	Packing Instruction	When the temperature of the Resin is below 50°C; pack the material as per the instructions