

SNO	PARAMETER	SPECIFICATION
1	Appearance	Light yellow to brownish yellow liquid
2	Viscosity @ 25°C	450 $\pm$ 90 cps
3	Specific Gravity	1.04 $\pm$ 0.01
4	Acid Value (mgKOH/Gm)	10 $\pm$ 4
5	Monomer content (%)	50 $\pm$ 4
6	Gel Time @ 25°C Resin – 100 Gm; Cobalt Accelerator – 1.5 ml; Promotor 1.5 ml MEKP Catalyst – 1.5 ml	20 $\pm$ 8
5	Packing Instruction	When the temperature of the Resin is below 45°C; pack the material as per the instructions