

SNO	PARAMETER	SPECIFICATION
1	Appearance	Thixotropic yellow to light brownish yellow liquid. Free from agglomerates
2	Viscosity @ 25°C	4000+ <u>1</u> 200 cps
3	Acid Value (mgKOH/Gm)	10+ <u>4</u>
4	Gel Time @ 25°C Resin – 100 Gm; Accelerator – 1.5 ml MEKP Catalyst – 1.5 ml PROMOTOR - 1.5ml	25+ <u>1</u> 0
5	Packing Instruction	When the temperature of the Resin is below 45°C; pack the material as per the instructions