

SNO	PARAMETER	SPECIFICATION
1	Appearance	Thixotropic pale yellow to White color hazy liquid Free from agglomerates
2	Viscosity @ 25°C	9000 $\pm$ 2700 cps
3	Acid Value (mgKOH/Gm)	12 $\pm$ 4
4	Gel Time @ 25°C Resin – 100 Gm; Cobalt Accelerator – 1.5 ml; Promotor 1.5 ml MEKP Catalyst – 1.5 ml	18 $\pm$ 8
5	Flammability Test	Type 1
6	Packing Instruction	When the temperature of the Resin is below 50°C; pack the material as per the instructions