

SNO	PARAMETER	SPECIFICATION
1	Appearance	Clear light brownish pale yellow to yellow liquid
2	Viscosity @ 25°C	350 \pm 70 cps
3	Specific Gravity @ 27°C	1.04 \pm 0.01
4	Acid Value (mgKOH/Gm)	10 \pm 4
5	Monomer Content (%)	42 \pm 4
6	Gel Time @ 25°C Resin – 100 Gm; Cobalt Accelerator 1.5 ml; Promotor 1.5 ml & MEKP Catalyst – 1.5 ml	25 \pm 10
7	Packing Instruction	When the temperature of the Resin is below 45°C; pack the material as per the instructions