

SNO	PARAMETER	SPECIFICATION
1	Appearance	Cream to White Colored Opaque Liquid
2	Viscosity @ 25°C	800 \pm 200 cps
3	Specific Gravity @ 27°C	1.1 \pm 0.05
4	Acid Value (mgKOH/Gm)	10 \pm 4
5	Monomer Content (%)	38 \pm 4
6	Gel Time @ 25°C Resin – 100 Gm; Cobalt Accelerator – 1.5 ml; Promotor 1.5 ml MEKP Catalyst – 1.5 ml	25 \pm 10
7	Flammability Test	Type 1
8	Packing Instruction	When the temperature of the Resin is below 45°C; pack the material as per the instructions