

SNO	PARAMETER	SPECIFICATION
1	Appearance	Thixotropic yellow to light brownish yellow liquid Free from agglomerates
2	Viscosity @ 25°C	4000 $\pm$ 1200 cps
3	Acid Value (mgKOH/Gm)	10 $\pm$ 4
4	Gel Time @ 25°C Resin – 100 Gm; Cobalt Accelerator – 1.5 ml; Promotor 1.5 ml MEKP Catalyst – 1.5 ml	25 $\pm$ 10
5	Packing Instruction	When the temperature of the Resin is below 45°C; pack the material as per the instructions