

SNO	PARAMETER	SPECIFICATION
1	Appearance	Clear light brownish to brownish yellow liquid
2	Viscosity @ 25°C	250 ± 40 cps
3	Specific Gravity @ 27°C	1.07±0.01
4	Acid Value (mgKOH/Gm)	10±4
5	Monomer Content (%)	37±3
6	Gel Time @ 25°C Resin – 100 Gm; Cobalt Accelerator – 1.5 ml; Promotor 0.75 ml MEKP Catalyst – 1.5 ml	30±10
7	Packing Instruction	When the temperature of the Resin is below 45°C; pack the material as per the instructions